

材料暨工程實驗室-台中

試驗報告

報告編號: TB-22-03653
C-22-08087

頁數: 1 OF 1

報告日期: 111年07月20日

工程名稱: 自測

承包商: -----

委託單位: 瑞達特貿易有限公司

供料廠商: 瑞達特貿易有限公司

樣品名稱: 德國PFLEIDERER集團Wodego低甲醛塑合板/化妝粒片板Melamine Faced Chipboard(18mm)

送驗人員: 瑞達特貿易有限公司-謝佩珊

收件日期: 111年07月08日

試驗日期: 111年07月08日~111年07月20日

備註: 1.以上資料(樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、
收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
2.除非另有說明,此報告結果僅對測試之樣品負責
未經本公司事先書面同意,此報告不可部分複製
3.本樣品由SGS材料暨工程實驗室-台北(申請書號碼: HB-22-04956 C-22-21267,
收件日期: 111年07月06日)轉送至本實驗室執行本報告所示之試驗項目。

試驗結果:

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.2	0.05	CNS 2215(2017)
甲醛釋出量-平均值 (mg/L)	0.2	0.05	

註: 1.試驗結果若低於方法偵測極限值(MDL)之測定值以"N.D."表示;
若高於方法偵測極限值(MDL),但低於定量極限值(ODL)時,以"<0.2"表示,
並括號註明其實測值
2.N.D. = Not Detected / 未檢出
3.本試驗報告之試驗地點同實驗室地址

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號: TB-22-03654

C-22-08088

頁數: 1 OF 1

報告日期: 111年07月25日

工程名稱: 自測

承包商: -----

委託單位: 瑞達特貿易有限公司

供料廠商: 瑞達特貿易有限公司

樣品名稱: 德國PFLEIDERER集團Wodego低甲醛塑合板/
化妝粒片板Melamine Faced Chipboard(18 mm)

送驗人員: 瑞達特貿易有限公司-謝佩珊

收件日期: 111年07月08日

試驗日期: 111年07月08日~111年07月25日

備註: 1.以上資料(樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、
收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
2.除非另有說明,此報告結果僅對測試之樣品負責
未經本公司事先書面同意,此報告不可部分複製
3.本樣品由SGS材料暨工程實驗室-台北(申請書號碼: HB-22-04957 C-22-21268,
收件日期: 111年07月06日)轉送至本實驗室執行本報告所示之試驗項目。

試驗結果:

試驗項目	試驗結果			試驗方法
	測定項目	SAMPLE 1	SAMPLE 2	
防焰性	火源加熱時間(min)	2	2	CNS 11668(2008)
	餘焰時間(sec)	1	1	
	餘燼時間(sec)	1	1	
	炭化面積(cm ²)	44	47	

註: 1.試驗樣品厚度: SAMPLE 1為17.9 mm; SAMPLE 2為17.9 mm

#2.測試面為正面

3.本試驗之樣品不在TAF認證範圍內,故無法出具TAF標誌之報告

4.本試驗報告之試驗地點同實驗室地址

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-23-01380

C-23-05229

頁數：1 OF 1

報告日期：112 年 03 月 17 日

委託單位：瑞達特貿易有限公司

供料廠商：瑞達特貿易有限公司

樣品名稱：德國 PFLEIDERER 集團 Wodego 低甲醛塑合板/化妝粒片板 Melamine Faced Chipboard(18mm)

送驗人員：瑞達特貿易有限公司(謝佩珊)

收件日期：112 年 02 月 24 日

試驗日期：112 年 02 月 24 日 ~ 112 年 03 月 08 日


備註：1. 以上資料(樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供

2. 除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
耐衝擊性	CNS 2215 : 2017	無放射狀龜裂、 破壞及化粧層之剝離， 平均凹陷直徑 14.9mm

註：本試驗報告之測試地點於新北市五股區(新北產業園區)五權路 55 號。



吳俊漢

本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

試驗報告



報告編號：HB-23-07995

C-23-33919

頁數：1 OF 1

報告日期：112 年 10 月 31 日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard(18mm)
 送驗人員：瑞達特貿易有限公司(謝佩珊)
 收件日期：112 年 10 月 19 日
 試驗日期：112 年 10 月 19 日 ~ 112 年 10 月 27 日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
吸水厚度膨脹率(%)	CNS 2215 : 2017	8

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路 55 號。



本報告若有提供規範要求值時，該規範僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-23-07993

C-23-33917

頁數：1 OF 1

報告日期：112年10月31日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard(18mm)
 送驗人員：瑞達特貿易有限公司(謝佩珊)
 收件日期：112年10月19日
 試驗日期：112年10月19日 ~ 112年10月27日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
抗彎強度(N/mm ²)	CNS 2215:2017	21.0

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。



吳俊漢

本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/E-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-24-02596

C-24-10712

頁數：1 OF 1

報告發行日期：113年04月19日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard (18mm)
 送驗人員：瑞達特貿易有限公司 (謝佩珊)
 收件日期：113年03月27日
 試驗日期：113年03月27日 ~ 113年04月11日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
耐酸性	參考 CNS 2215 : 2017	表面無變色
耐鹼性		表面無變色

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。



本報告若有提供規範要求值時，該規範值僅供參考，最終之判定仍以委託單位實際要求為準。

報告簽署人



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-24-02591

C-24-10707

頁數：1 OF 1

報告發行日期：113 年 04 月 19 日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard (18mm)
 送驗人員：瑞達特貿易有限公司 (謝佩珊)
 收件日期：113 年 03 月 27 日
 試驗日期：113 年 03 月 27 日 ~ 113 年 04 月 10 日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
密度(g/cm ³)	CNS 2215 : 2017	0.69

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路 55 號。

本報告若有提供規範要求值時，該規範值僅供參考，最終之判定以委託單位實際要求為準。

報告簽署人



This document is issued by the Company subject to its General Conditions of Service printed overseas, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-23-07994

C-23-33918

頁數：1 OF 1

報告日期：112 年 10 月 31 日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard(18mm)
 送驗人員：瑞達特貿易有限公司(謝佩珊)
 收件日期：112 年 10 月 19 日
 試驗日期：112 年 10 月 19 日 ~ 112 年 10 月 27 日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
濕潤抗彎強度 A 試驗(N/mm ²)	CNS 2215 : 2017	8.9

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路 55 號。



吳俊漢

本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-24-02595

C-24-10711

頁數：1 OF 1

報告發行日期：113年04月19日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化粧粒片板 Melamine Faced Chipboard (18mm)
 送驗人員：瑞達特貿易有限公司 (謝佩珊)
 收件日期：113年03月27日
 試驗日期：113年03月27日 ~ 113年04月11日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
內聚強度(N/mm ²)	參考 CNS 2215:2017	0.4

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。



本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：HB-24-02594

C-24-10710

頁數：1 OF 1

報告發行日期：113年04月19日

委託單位：瑞達特貿易有限公司

供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.

樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/

化妝粒片板 Melamine Faced Chipboard (18mm)

送驗人員：瑞達特貿易有限公司 (謝佩珊)

收件日期：113年03月27日

試驗日期：113年03月27日 ~ 113年04月11日

備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及

試驗日期除外)及下述報告內容標示#處係由顧客提供

2. 除非另有說明，此報告結果僅適用於收取之試驗件

未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
木螺釘保持力(N)	參考 CNS 2215 : 2017	533

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。



本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

試驗報告



報告編號：HB-24-02592

C-24-10708

頁數：1 OF 1

報告發行日期：113年04月19日

委託單位：瑞達特貿易有限公司
 供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co., Ltd.
 樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/
 化妝粒片板 Melamine Faced Chipboard (18mm)
 送驗人員：瑞達特貿易有限公司 (謝佩珊)
 收件日期：113年03月27日
 試驗日期：113年03月27日 ~ 113年04月11日
 備註：1. 以上資料(會驗人員、試驗方法、試驗數量、收件日期及
 試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
含水率(%)	CNS 2215 : 2017	8.1

註：1. 樣品描述：化粧粒片板。

2. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。

本報告若有提供規範要求值時，該規範值僅供參考，最終之判定應以委託單位實際要求為準。

報告簽署人



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：KV-24-03224

頁數：1 OF 1

報告發行日期：113 年 04 月 18 日

委託單位：瑞達特貿易有限公司

供料廠商：瑞達特貿易有限公司 Red Dot Furniture Trade Co.,Ltd.

樣品名稱：德國 PFLEIDERER 集團 Wodego F****低甲醛塑合板/化妝粒片板 Melamine Faced Chipboard (18mm)

送驗人員：瑞達特貿易有限公司(謝佩珊)

收件日期：113 年 04 月 02 日

試驗日期：113 年 04 月 02 日~113 年 04 月 18 日

備註：1.以上資料(會驗人員、試驗方法、試驗數量、收件日期及

試驗日期除外)及下述報告內容標示#處係由顧客提供

2.除非另有說明，此報告結果僅適用於收取之試驗件

未經本公司事先書面同意，此報告不可部分複製

3.本樣品由 SGS 材料暨工程實驗室-台北(申請書號碼：HB-24-02598 C-24-10714，

收件日期：113 年 03 月 27 日)轉送至本實驗室執行本報告所示之試驗項目

試驗結果：

試驗項目		測試方法	試驗結果	#規範 CNS 2215：2017 要求值
耐變褪色性 (WV type, 48 小時)	外觀	CNS 2215：2017	無龜裂、鼓脹等缺點	不得有龜裂、鼓脹等缺點
	色差 ΔE^*		0.96	變色用灰色標 4 號以上或 色差 3.0 以下

註：1.試驗機型式：SUGA U48

2.使用光源：Ultraviolet Carbon Arc

3.濾鏡：球型玻璃

4.測試條件：黑板溫度： $(63\pm 3)^{\circ}\text{C}$ 相對濕度： $(30\pm 5)\%\text{R.H.}$

測試週期：連續照光無噴水

5.色差條件：波長：360nm~780nm

光源：CIE illuminant D65

標準視角： 10°

6.樣品描述：粒片板。

7.本實驗室執行試驗之地點同實驗室地址

本報告若有提供規範值，該規範值僅供參考，合格判定應以委託單與實際要求為準

This document is issued by the Company subject to its General Conditions of Sale and is not valid unless accompanied by the original request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.