



綠建材標章證書

綠建材標章證書字號：GBM0102343（續）

申請廠商：育德實業股份有限公司

申請人：廖文嘉

廠商地址：臺北市士林區中山北路6段88號5樓

產品名稱：化粧粒片板

產品型號：K25-厚度 25mm F1 木紋色-天然栓木 37769、K25-厚度 25mm F1 木紋色-沼區櫟木 37717、
K18-厚度 18mm F1 素色-白色 1101、K18-厚度 18mm F1 素色-白色 1110、
K18-厚度 18mm F1 素色-白色 1500、K18-厚度 18mm F1 素色-鑽石壓紋白 1570、
K18-厚度 18mm F1 素色-鑲帛 2507、K18-厚度 18mm F1 素色-灰色 2112、
K18-厚度 18mm F1 木紋色-典雅櫻桃 37967、K18-厚度 18mm F1 木紋色-經典榆木 37965、
K18-厚度 18mm F1 木紋色-泥櫟 34137、K18-厚度 18mm F1 木紋色-雷莫櫟木 34138、
K18-厚度 18mm F1 木紋色-沙櫟木 34139、K18-厚度 18mm F1 木紋色-雪白榆木 34143、
K18-厚度 18mm F1 木紋色-瓦雷白松 37744、K18-厚度 18mm F1 木紋色-天然栓木 37769、
K18-厚度 18mm F1 木紋色-黃檀木 38995、K18-厚度 18mm F1 木紋色-摩卡年輪 K5411

生產廠址：5071 Wals-Siezenheim, Kaindlstraße 2, Austria


有效期限：自110年3月16日至113年3月15日止

合格項目：健康綠建材（E2逸散）

試驗項目：甲醛（HCHO）逸散速率
總揮發性有機物質（TVOC）逸散速率

內政部 部長 徐國勇

中華民國 109 年 12 月 23 日



試驗報告



報告編號：TB-22-01601

C-22-03800

頁數：1 OF 1

報告日期：111年03月31日

工程名稱：自測

承包商：----

委託單位：育德實業股份有限公司

供料廠商：----

樣品名稱：M.KAINDL OG 化粧粒片板

加註項目：K18厚度18 mm 甲醛釋出標準F1

送驗人員：育德實業股份有限公司-林榆芬

收件日期：111年03月24日

試驗日期：111年03月24日~111年03月31日

備註：1.以上資料(樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、
收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.3	0.05	CNS 2215(2012)
甲醛釋出量-平均值 (mg/L)	0.3	0.05	

註：1.試驗結果若低於方法偵測極限值(MDL)之測定值以"N.D."表示；

若高於方法偵測極限值(MDL)，但低於定量極限值(QDL)時，以"<0.2"表示，

並括號註明其實測值

2.N.D. = Not Detected / 未檢出

3.本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告

報告編號： TB-22-01602
C-22-03801頁數： 1 OF 1
報告日期： 111年05月04日

工程名稱：自測
 承 包 商：-----
 委託單位：育德實業股份有限公司
 供料廠商：M.KAINDL
 樣品名稱：M.KAINDL OG 化粧粒片板
 加註項目：K18厚度18 mm 甲醛釋出標準F1
 送驗人員：育德實業股份有限公司-林榆芬
 收件日期：111年03月24日
 試驗日期：111年03月24日~111年05月04日
 備註：1.以上資料（樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、
 收件日期及試驗日期除外）及下述報告內容標示#處係由顧客提供
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗結果	試驗方法
厚度 (mm)	18.2	CNS 2215(2017)
密度 (g/cm ³)	0.72	
含水率 (%)	8	
抗彎強度 (N/mm ²)	19.0	
濕潤抗彎強度-A試驗 (N/mm ²)	10.5	
抗彎彈性模數 (N/mm ²)	3017	
耐衝擊性 (W ₂ -500, 100 cm)	無龜裂、破壞及剝離的情形 (平均凹陷直徑 14 mm)	
吸水厚度膨脹率 (%)	4	
內聚強度 (N/mm ²)	0.4	
平面抗拉強度 (N/mm ²)	0.9	
紅色蠟筆之耐污染性	污染用灰色標 4-5 級	
耐酸性 (5 %醋酸水溶液)	不變色	
耐鹼性 (1 %碳酸鈉水溶液)	不變色	

註：1.本試驗報告厚度、密度、含水率、抗彎強度及耐衝擊性試驗為TAF認證範圍，其餘則非
 2.本試驗報告之試驗地點同實驗室地址
 3.試驗報告TB-22-01602 C-22-03801與TB-22-02340 C-22-05443為同一委託案件，
 試驗報告TB-22-01602 C-22-03801收件日期為111年03月24日。

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



材料暨工程實驗室-台中

試驗報告



報告編號：TB-22-01603

C-22-03802

頁數：1 OF 1

報告日期：111年04月06日

工程名稱：自測

承包商：-----

委託單位：育德實業股份有限公司

供料廠商：KAINDL

樣品名稱：M.KAINDL OG 化粧粒片板

加註項目：K18厚度18 mm 甲醛釋出標準F1

送驗人員：育德實業股份有限公司-林榆芬

收件日期：111年03月24日

試驗日期：111年03月24日~111年04月06日

備註：1.以上資料（樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、

收件日期及試驗日期除外）及下述報告內容標示#處係由顧客提供

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗結果			試驗方法
	測定項目	SAMPLE 1	SAMPLE 2	
防焰性	火源加熱時間(min)	2	2	CNS 11668(2008)
	餘焰時間(sec)	0	0	
	餘燼時間(sec)	0	0	
	炭化面積(cm ²)	31	36	

註：1.試驗樣品厚度：SAMPLE 1為17.8 mm；SAMPLE 2為17.8 mm

2.測試面為正面

3.本試驗之樣品不在TAF認證範圍內，故無法出具TAF標誌之報告

4.本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.